



PRICE RESEARCH, LTD.
 3511 Stadium Drive
 Kansas City, Missouri 64129
 Phone/Fax (816) 924-5955
 www.priceresearchltd.com

PRODUCT DATA

PRICE TILE AND MASONRY PROTECTOR (PTMP)

PRODUCT NAME: PRICE TILE AND MASONRY PROTECTOR (PTMP)

MANUFACTURER: PRICE RESEARCH, LTD.
 3511 Stadium Drive
 Kansas City, MO 64129 • Phone: (816) 924-5955

PRODUCT DESCRIPTION:

PRICE TILE AND MASONRY PROTECTOR (PTMP) is specially designed to protect stone, tile, brick masonry, concrete masonry and terrazzo surfaces. PTMP provides excellent protection against food oil (oleophobic), grease, lipstick, paints and other resinous materials.

RECOMMENDED FOR:

- Kitchens • Restaurants • Shopping Centers • Food Courts • Driveways • Amusement Parks
- Zoo • Sports Arenas

EXCELLENT FOR:

- Brick Masonry • Concrete Masonry • Brick and Concrete Pavers • Tiles • Stone • Terrazzo
- Limestone • Marble

PRICE TILE AND MASONRY PROTECTOR will not alter natural appearance.

FEATURES:

1. Easy to maintain.
2. Protects against oil (oleophobic) and water.
3. No surface buildup or gloss.
4. High degree of vapor transmission.

LIMITATIONS:

1. Not recommended for painted or asphaltic surfaces.
2. Protect glass, synthetic and reflective materials.
3. Solvent odor may preclude interior use.
4. Will not bridge gaps, cracks and structural defects.
5. Surface textures may contribute to an inconsistent final appearance.
6. Recommended to be used between 40°F to 90°F air and surface temperature.

TECHNICAL DATA:

Form	Clear liquid.
Specific gravity	0.9
Flash point	75°F
Wt/gal	7.5 lbs.
pH	None
Moisture vapor transmission rate (ASTM E 96-90)	48gms.
V.O.C. Content (EPA Method 24)	Less than 170 gms/liter
Permeability (ASTM D-1653)	Min. 80% breathable.
Efflorescence (NBS - 883)	Highly resistance.

Continued on back

APPLICATION: TEST FIRST

Surface Preparation: Surfaces to be treated should be free of dirt, oil and moisture.

1. New concrete, mortar, stucco, etc. should be allowed to cure at least 14 days before application of PTMP.
2. May be applied with low pressure (40 psi or less) spray equipment or brush or roller.
3. When using low pressure spray equipment, apply a light mist coat to break the surface tension. This allows for good penetration. Repeat the process with flood coat (4 to 6 inch run down for vertical surface). For horizontal surface avoid puddling.
4. CAUTION: Do not alter the material as supplied. Avoid using rubber hoses, rubber seals, etc. as the solvent may have adverse effect with these materials causing staining and discoloration.

COVERAGE RATE

<u>Substrate</u>	<u>Sq. Ft. Per Gallon</u>
Brick Masonry	150 to 200 sq.ft.
Concrete Masonry	100 to 150 sq.ft.
Stones (Limestone, Marble, Sandstone, etc.)	100 to 150 sq.ft.
Brick Paver	150 to 200 sq.ft.
Concrete Paver	100 to 150 sq.ft.
Clay Tile	150 to 200 sq.ft.
Terrazzo	150 to 200 sq.ft.

CLEAN UP: Use mineral spirits to clean tools and equipment.

LIMITED WARRANTY:

Price Research, Ltd. has no control over the storage, handling or use of this product, thus the guarantee is limited to the purchase price of defective material only.

TECHNICAL SERVICE: Call Price Research, Ltd. at (816) 924-5955 and ask for Technical Service.