



PRICE RESEARCH, LTD.
 3511 Stadium Drive
 Kansas City, Missouri 64129
 Phone/Fax (816) 924-5955
 www.priceresearchltd.com

PRODUCT DATA

PRICE-SEAL WET LOOK

PRODUCT NAME: PRICE-SEAL WET LOOK

MANUFACTURER: PRICE RESEARCH, LTD.
 3511 Stadium Drive
 Kansas City, MO 64129
 Phone: (816) 924-5955

PRODUCT DESCRIPTION:

PRICE-SEAL WET LOOK is a unique blend of polymer, combined with evaporating media to provide high performance, high gloss, non-yellowing, breathable, long lasting protective coating.

Excellent For:

- Wet Look on paver
- Wet Look on clay tile
- Wet Look on vertical brick masonry
- Wet Look on block surface
- Wet Look on aggregate concrete surface
- Wet High Gloss Look on any concrete surface
- Wet Look on any colored concrete and colored blocks
- Wet Look on any vertical stone surface

Basic Use:

- Water barrier for masonry surfaces.
- Excellent for concrete masonry protection.
- Spalling and cracking are reduced or eliminated.
- Excellent for tile, stucco, architectural concrete.
- Excellent for exterior and interior surfaces (vertical and horizontal).

PRICE-SEAL WET LOOK meets and surpasses ASTM Spec. C-309 Type 1.
 Meets AASHTO-M-148 Type 1D.

Limitations:

PRICE-SEAL WET LOOK provides high gloss protective coating for outdoor or indoor use, in case of water spillage, it may become slippery.

TECHNICAL DATA:

Color Water Clear
 pH Neutral
 Drying Time To touch about 25 minutes
 Cold Stability Excellent
 Flash Point 83° (Tag close cup)

Continued on back

Resistance To: (Dry Film)

Acid	Excellent
Alkali	Excellent
Gasoline	Excellent
Food Acid	Excellent
Airborne Pollutants	Excellent
Ultra Violet Resistance	Excellent
Hydraulic Fluid	Excellent

DIRECTION FOR USE: TEST FIRST

Surface Preparation:

New Masonry: Surface should be free of all dust, debris, oil and tar. All joint sealants, caulks and patching should be in place before treatment.

Old Masonry: Remove dirt, dust, tar, oil, etc. with pressure wash and PRICE NON-ACID MASONRY CLEANER. Repair cracked areas, except hairline cracks.

Application: Horizontal & Vertical Surfaces

1. Use roller, brush or low-pressure sprayer.
2. Coat surface uniformly, leaving no pinholes or gaps at rate shown on coverage table below.
3. Under normal conditions, surface will dry in 30 minutes.
4. Recommended to be applied at 40° to 90°F outside temperature. At cooler temperature, product will take longer to dry than at higher temperature.
5. For desired Higher Gloss, a second coat is recommended.

COVERAGE TABLE

Exact coverage will depend upon the porosity of the surface and density.

<u>TYPE OF SURFACE</u>	<u>APPROXIMATE COVERAGE</u> (Sq.Ft. / Gal./One Coat)	<u>SUGGESTED APPLICATION</u>
Brick Masonry	75 - 100	One Coat
Exposed Aggregate	75 - 125	Two Coats
Paver (Clay Tile)	100 - 125	One to Two Coats
Block	50 - 75	Two Coats
Concrete	100 - 150	One to Two Coats

Clean Up:

Use xylene to clean tools and equipment.

Precautions:

1. Use in well ventilated areas only.
2. Do not dilute or alter PRICE-SEAL WET LOOK.
3. Do not use at temperature below 40°F (4°C).

AVAILABILITY AND COST:

Please contact Price Research, Ltd.
Phone: (816) 924-5955

LIMITED GUARANTEE:

Price Research, Ltd. has no control over the storage, handling or use of this product, thus the guarantee is limited to the purchase price of the defective material only.

TECHNICAL SUPPORT:

Call Price Research, Ltd. at (816) 924-5955 and ask for Technical Service.